

Close

Web of Science
Page 1 (Records 1 -- 1)

Print



Record 1 of 1

Title: Poisson's Ratio of Closed-Cell Aluminium Foams**Author(s):** Kovacik, J (Kovacik, Jaroslav); Marsavina, L (Marsavina, Liviu); Linul, E (Linul, Emanoil)**Source:** MATERIALS **Volume:** 11 **Issue:** 10 **Article Number:** 1904 **DOI:** 10.3390/ma11101904 **Published:** OCT 2018**Times Cited in Web of Science Core Collection:** 1**Total Times Cited:** 1**Usage Count (Last 180 days):** 0**Usage Count (Since 2013):** 0**Cited Reference Count:** 39

Abstract: A nondestructive impulse excitation technique was used to investigate Poisson's ratio of powder metallurgical pure closed-cell aluminium foams according to ASTM E 1876 within the foam density range of 0.430-1.390 gcm⁻³. Instead of a constant value of 0.34, as according to Gibson and Ashby's assumption for the Poisson's ratio of metallic foams, the decrease of the Poisson's ratio with decreasing foam density was observed. Observed Poisson's ratio data were in the range of 0.21-0.34. To check the validity of the results, the Young's modulus was calculated using Poisson's ratio and its dependence on relative density was successfully modelled using the usual power law function with characteristic exponent of 1.72 +/- 0.1. This confirms that the obtained experimental results for Poisson's ratio are valid. Finally, rule of mixture and percolation theory were used to model the observed decrease of Poisson's ratio with increasing porosity.

Accession Number: WOS:000448658400118**PubMed ID:** 30301257**Language:** English**Document Type:** Article**Author Keywords:** aluminium foam; closed-cell foam; Poisson's ratio; porosity; nondestructive testing; modulus of elasticity**KeyWords Plus:** MECHANICAL-PROPERTIES; ELASTIC PROPERTIES; PLASTIC BEHAVIOR; METAL FOAMS; CONDUCTIVITY; MODULUS**Addresses:** [Kovacik, Jaroslav] Slovak Acad Sci, Inst Mat & Machine Mech, Dubravskacesta 9, Bratislava 84513, Slovakia.

[Marsavina, Liviu; Linul, Emanoil] Politehn Univ Timisoara, Dept Mech & Strength Mat, 1 Mihai Viteazu Ave, Timisoara 300222, Romania.

Reprint Address: Kovacik, J (reprint author), Slovak Acad Sci, Inst Mat & Machine Mech, Dubravskacesta 9, Bratislava 84513, Slovakia.**E-mail Addresses:** ummsjk@savba.sk; liviu.marsavina@upt.ro; emanoil.linul@upt.ro**Author Identifiers:**

Author	ResearcherID Number	ORCID Number
Kovacik, Jaroslav	K-2556-2013	0000-0002-6970-0406
LINUL, Emanoil		0000-0001-9090-8917

Publisher: MDPI**Publisher Address:** ST ALBAN-ANLAGE 66, CH-4052 BASEL, SWITZERLAND**Web of Science Categories:** Materials Science, Multidisciplinary**Research Areas:** Materials Science**IDS Number:** GY5XW**ISSN:** 1996-1944**29-char Source Abbrev.:** MATERIALS**ISO Source Abbrev.:** Materials**Source Item Page Count:** 11**Funding:**

Funding Agency	Grant Number
Romanian Ministry of Research and Innovation, CCCDI - UEFISCDI	PN-III-P1-1.2-PCCDI-2017-0391/CIA_CLIM
Slovak Research and Development Agency	APVV-0692-12 APVV-17-0580 SK-RO-0014-12 653/2013
Slovak Grant Agency (VEGA grants)	2/0152/17 2/0044/17

This research was funded by the grant of the Romanian Ministry of Research and Innovation, CCCDI - UEFISCDI, project number PN-III-P1-1.2-PCCDI-2017-0391/CIA_CLIM-Smart buildings adaptable to the climate change effects, within PNCDI III, Slovak Research and Development Agency under bilateral agreement between UPT and SAS, contract no. SK-RO-0014-12 and 653/2013, Slovak Research and Development Agency grants APVV-0692-12, APVV-17-0580 and Slovak Grant Agency (VEGA grants 2/0152/17 and 2/0044/17).

Open Access: DOAJ Gold**Output Date:** 2019-01-04

Close

Web of Science
Page 1 (Records 1 -- 1)

Print



Clarivate

Accelerating innovation

© 2019 Clarivate

Copyright notice

Terms of use

Privacy statement

Cookie policy

Sign up for the Web of Science newsletter

Follow us

